


# Oil★Star® Detonators

## A-96

PRODUCT INFORMATION BROCHURE

### PROPERTIES

A-96	
Shell Length	61 mm / 2.4 "
Base Charge	11 grains RDX (0.713 gram)
No-Fire Current ( approx.) (Based on a constant voltage for 1 minute)	0.2 amperes
All-Fire Current ( approx.)	0.8 amperes
Minimum Firing Current (approx.)	0.5 amperes
Resistors in Series with Bridgewire	(2) 27 ohm
Leg to Leg Resistance Plus 0.032 for each foot of duplex wire	51 to 60 ohm + 0.27/0.32 ohm
Pressure Resistance at 325°F	15,000 PSI/1 hr.
High Temperature Performance	1 hr. at 325°F
Electrostatic Sensitivity Energy Value (Double leg to shell capacitor discharge energy level)	781 mJ



### ADVANTAGES

- Antistatic sleeve and spark gap protect against static electricity.
- Leg wires are high temperature Teflon insulated 22 gauge four feet long copper leg wires.

### STANDARD TECHNICAL DESCRIPTION

High pressure resistorized instantaneous RDX detonator



**AUSTIN POWDER**

Austin Powder Company, 25800 Science Park Drive

Phone: 1-800-321-0752 | Fax: 1-216-464-4418 | Email: info@austinpowder.com | www.austinpowder.com

# Oil★Star Detonators

## A-96

### STANDARD PACKAGING DETAILS

Oil★Star A-96 detonators are packaged 50 detonators per inner package, 500 detonators per case.

### STORAGE

Store in accordance with all applicable local, state, provincial and federal laws.

### SHELF LIFE

For optimum accuracy, use within five years from date of manufacture under good storage conditions.

### TRANSPORTATION DATA

#### UN CLASSIFICATION

Shipping Name: Detonators, electric, for blasting

Class & Division: 1.4B

ID Number: UN 0255

#### US DOT REFERENCE NUMBER

EX-199511002



**Disclaimer of Warranties and Limitations of Liabilities:** Products described in this bulletin are sold by Austin Powder Company without warranty; express, implied or statutory or as to MERCHANTABILITY, except as expressly stated in Austin Powder's straight bill of lading. Under no circumstances shall seller be liable for loss of anticipated profits, consequential damages or incidental damages.

© 2020 Austin Powder Company. All rights reserved.

For more information and service locations in your area, please contact Austin Powder Company's headquarters:



## AUSTIN POWDER

Austin Powder Company, 25800 Science Park Drive

Phone: 1-800-321-0752 | Fax: 1-216-464-4418 | Email: [info@austinpowder.com](mailto:info@austinpowder.com) | [www.austinpowder.com](http://www.austinpowder.com)

04/02 | r 01/31/2020